

Miragrid[®] 3XT

Miragrid[®] 3XT geogrid is composed of high molecular weight, high tenacity polyester multifilament yarns which are woven in tension and finished with a PVC coating. Miragrid[®] 3XT geogrid is inert to biological degradation and resistant to naturally encountered chemicals, alkalis, and acids.

Mechanical Properties	Test Method	Unit	Minimum Average Roll Value
			Machine Direction
Tensile Strength (at ultimate)	ASTM D6637	kN/m (lbs/ft)	51.1 (3500)
Tensile Strength (at 5% strain)	ASTM D6637	kN/m (lbs/ft)	15.4 (1056)
Creep Reduced Strength	ASTM D5262	kN/m (lbs/ft)	32.3 (2215)
Long Term Allowable Design Load ¹	GRI GG-4(b)	kN/m (lbs/ft)	28.0 (1918)

¹ NOTE: Long Term Allowable Design values are for sand, silt and clay

Physical Properties	Test Method	Unit	Typical Value
Grid Aperture Size (machine direction)	--	mm (in)	22.2 (0.875)
Grid Aperture Size (cross machine direction)	--	mm (in)	25.4 (1.0)
Mass/Unit Area	ASTM D5261	g/m ² (oz/yd ²)	278.0 (8.2)
Roll Dimensions (width x length)	--	m (ft)	3.6 (12) x 45.7 (150)
Roll Area	--	m ² (yd ²)	164.5 (200)
Estimated Roll Weight	---	kg (lbs)	59 (130)

Disclaimer: TenCate assumes no liability for the accuracy or completeness of this information or for the ultimate use by the purchaser. TenCate disclaims any and all express, implied, or statutory standards, warranties or guarantees, including without limitation any implied warranty as to merchantability or fitness for a particular purpose or arising from a course of dealing or usage of trade as to any equipment, materials, or information furnished herewith. This document should not be construed as engineering advice.

© 2011 TenCate Geosynthetics North America
 Miragrid[®] is a registered trademark of Nicolon Corporation

