

Flexible Latex Cement Additive

DS-FA 2-17

PRODUCT

R-FlexAd™

MANUFACTURER

R-Crete Inc
 P.O. Box 80286
 Rancho Santa Margarita, CA 92688
 949-888-8401 Fax 949-858-5720



DESCRIPTION: R-FlexAd is a highly flexible, latex additive for Portland cement mortars. It improves flexibility, impact resistance, flexural bond strength and water resistant properties. R-FlexAd is an extremely versatile product with a wide variety of uses with many different products.

USES: R-FlexAd is added as the complete or partial replacement of the mix water in Portland cement mortar, grouts and concrete mixes. It is primarily added to bonding mortars and waterproof coatings. R-FlexAd is used where high impact resistance, flexural bond strength and water repellent properties are essential (ie: paver installation, pre-cast cap installations, bonding to substrates with high movement).

R-FlexAd is typically added to the following products:

- | | |
|---------------------------|----------------------|
| -VBM | -MAC Scratch & Brown |
| -Poly VBM (LFT, 300, 500) | -Poly Water Stop |
| -VBM Bonder | -Dry Pack (3:1) |
| -VBM Poly Thin Brick | -Deck Mud |
| -VBM Thinset | |

ADVANTAGES:

Adds water resistance, flexibility and impact resistance to bonding mortars and grouts.
 Improves water resistance and flexibility for cement based waterproof coatings – CemCoat Seal
 Versatile – Maybe used in a wide variety of mortars, coatings and applications.
 Safe and easy to use. Non-hazardous and non-flammable.
 Reduces cracking.

TECHNICAL DATA:

Polymer: Water based Latex
 Color: white
 Ph: 7-8
 VOC: zero

Flammability: Non flammable

Addition: Will vary with application and product. Typically 25-100% replacement of mix water.

STORAGE: Store in a cool dry area out of direct sunlight. Protect from freezing. Shelf life is expected to be 3 years when stored in unopened containers in temperatures between 40°F (4°C) and 90°F (32°C).

PACKAGING: R-FlexAd is available in 1 gallon (3.78 L) and 5 gallon (19 L) plastic pails.

LIMITATIONS:

Limitations:

- Not recommended for green or water sensitive natural stone.
- Substrate must be sound-any cracks or excessive movements may extend through mortar or cause bond failure.
- Avoid applications in high heat, wind or cold expected 40 °F prior to cure.
- Follow ANSI installation requirements.
- Bring expansion joints and control joints through veneers to the surface.
- Always perform quality control test procedures before and during application

SUITABLE SUBSTRATES: Properly prepared-

- Concrete
- Cement mortar beds
- Concrete masonry
- Cement plaster
- Brick masonry
- Some asphalt adhesives*
- R-Lastic coated substrates
- Cement backer board*
- Gypsum wall board*
- Existing ceramic tile and stone*
- Exterior grade plywood*
- Vinyl flooring*
- Plastic laminate*

*Interior use only

* Consult backer board manufacturer for suitability and instructions for the intended application.

A substrate suitable for bonding does not mean it is recommended for all veneers or applications.

*Properly prepared.

*Pre installation tests required.

SURFACE PREPARATION:

Substrates must be structurally sound, suitable for the application. All surfaces must be clean and free from any dirt, dust, oil, grease, curing agents, bond breakers, loose paint or any substance that may reduce bond. Smooth surfaces must be roughened. Dampen substrates just prior to application. This is especially important on excessively absorptive substrates or when applications are in direct sunlight. Surface temperatures of substrate must be between 40°F (4°C) and 90°F (32°C). Bring all expansion joints to the surface. Do not cover expansion joints with mortar. Follow ANSI Specifications. Substrates must be plumb and true within ¼" (6mm) in 10 Ft. (3 m).

Mixing: Stir R-FlexAd just prior to use. It is preferable to add the dry mortar powder into the R-FlexAd liquid. Adjust the consistency of the mix with R-FlexAd. When mixing take care not to whip excess air into the mortar. If using a drill, use at low speed (< 300 rpm) and with a blade that does not create high air. High air content will lower strength.

APPLICATION: See OBP product data sheets for detailed application instructions.

CLEAN UP: Clean tools and surrounding area with water prior to curing.

AVAILABILITY: R-FlexAd is available at local building supply yards.

Other markets contact:
R-CRETE INC.
949-888-8401 for a local distributor.
www.rcrete.com

Warranty: The technical information and usage statements are based on our best knowledge. The contents of the specification sheet are presented for informational purposes only and do not constitute responsibility for their use. The manufacturer will replace only that material which is proven defective due to quality of the components or the manufacturing process.

The information and recommendations made here in are based on our own research and the research of others. All information is believed to be accurate. However purchasers should make their own test to determine the suitability of product for their particular application. Our only warranty shall be that of replacing the product due to manufacturing defects.